

APPLIED TECHNICAL SERVICES, INCORPORATED



1049 Triad Court, Marietta, Georgia 30062 • (770) 423-1400 Fax (770) 424-6415

CPSIA TEST REPORT

ATS JOB # 342190

PURCHASE ORDER # CREDIT CARD

Prepared for

JOHN HARKINS LANDES, INC. 7600 RENWICK DR. HOUSTON, TX 77081

CPSIA Lead Prepared by	
	J. Joris, Senior Chemist
CPSIA Phthalates Prepared by	
1	S. Tan, Senior Chemist
CPSIA Report Approved by	
1 11 V	J. Burmeister, Manager

This report may not be reproduced except in full without the written approval of ATS. This report represents interpretation of the results obtained from the test specimen and is not to be construed as a guarantee or warranty of the condition of the entire material lot. If the method used is a customer provided, non-standard test method, ATS does not assume responsibility for validation of the method. Measurement uncertainty available upon request where applicable.

Professional Engineers and Scientists

Design • Consulting • Testing and Inspection

Members in AAFS, ACS, ASM, ASME, ASNT, ASQC, ASTM, AWS, FSCT, IAAI, NACE, NCSL, NFPA, SAFS, TAPPI
GEORGIA SOCIETY OF PROFESSIONAL ENGINEERS, NATIONAL SOCIETY OF PROFESSIONAL ENGINEERS

CHEMICAL TEST REPORT								
Ref.	342190	Date:	October 5, 2020	Page 1	of	4		

Conclusion:

The submitted samples were tested under the following requirements that have been requested by the customer.

Sample ID	<u>Requirement</u>	Results	
 Black Polyester Fabric Black Elastic 	CPSIA Section 101 CPSC-CH-E1001-08 CPSC-CH-E1002-08 – total lead content limits CPSC-CH-E1003-09	Pass	
 White Filter Lining 	CPSIA Section 108 CPSIA regulated phthalates	Pass	

CHEMICAL TEST REPORT Ref. 342190 Date: October 5, 2020 Page 2 of 4

Purchase Order # Credit Card

Subject

CPSIA lead and phthalate analysis was performed on the following items: Black Polyester Fabric, Black Elastic and White Filter Lining.

Material

Non – Metals

Background and Objective

16 C.F.R. 1303 requirements for lead CPSIA Section 101 requirements for lead CPSIA Subsection 108(a) requirement for phthalates

Test Procedure

- Lead Analysis (Table I):

Samples prepared using microwave digestion techniques per CPSC-CH-E1002-08. ICP atomic emission techniques utilized to analyze for lead as per ASTM E1479-16.

- Phthalate Analysis (Table II):

GC/MS was used to identify and quantify the phthalate compounds according to CPSC-CH-C1001-09.4.

Results and Conclusions

See Results in Appendix I.

CHEMICAL TEST REPORT

Ref. 342190 **Date:** October 5, 2020 **Page** 3 **of** 4

APPENDIX I Results

Table I: Composition, ppm (mg/kg)

Component	ATS#	Total Pb	Pass/Fail
Black Polyester Fabric	1	<4	Pass
Black Elastic	2	<4	Pass
White Filter Lining	3	<4	Pass

Requirements for children's consumer products manufactured after August 14, 2011: Lead in accessible substrates 100 ppm maximum; Lead in paints and similar surface coatings 90 ppm maximum.

Table II: Composition, ppm (mg/kg)

Component	ATS#	DPENP§	DHEXP§‡ (DnHP)	DCHP§	DIBP§	DEHP§‡	DnBP§‡	BBP§‡	DINP§‡	DIDP‡	DNOP	Pass/ Fail
Max CPSIA Phthalate Requirement	-	1000 Max.	1000 Max.	1000 Max.	1000 Max.	1000 Max.	1000 Max.	1000 Max.	1000 Max.	1000 Max.	1000 Max.	_
Black Elastic	2	*N.D.	*N.D.	*N.D.	*N.D.	*N.D.	*N.D.	*N.D.	*N.D.	*N.D.	*N.D.	Pass

*N.D. – None Detected <50 ppm: Di-N-Pentyl Phthalate (DPENP), Di-N-Hexyl Phthalate (DHEXP), Dicyclohexyl Phthalate (DCHP), Diisobutyl Phthalate (DIBP), Di-Ethyl Hexyl Phthalate (DEHP), Di-N-Butyl Phthalate (DnBP), Butyl Benzyl Phthalate (BBP), Di-Isononyl Phthalate (DINP), Di Isodecyl Phthalate (DIDP) and Di-n-Octyl Phthalate (DnOP) \$CPSIA Subsection 108(a) requirement for phthalates

‡CA Prop 65 requirements for phthalates



CHEMICAL TEST REPORT

Ref. 342190 **Date:** October 5, 2020 **Page** 4 **of** 4

APPENDIX II Photos





Figure 1 Figure 2



Figure 3